

SUPER GLUE PART NO. 49431

PHYSICAL PROPERTIES

MONOMER (Liquid)

Base Compound Ethyl Cyanoacrylate
 Appearance..... Colorless Liquid
 Viscosity (cps @ 68°F) 100 cP
 Specific Gravity (g/cc) 1.06
 Flash Point (TCC) 185°F
 Shelf Life @ 40°F..... One year in unopened containers
 Setting Time: (68°F, 65%R.H.)
 Metal/Metal..... 20 seconds
 Plastic/Plastic 7 seconds
 Rubber/Rubber 5 seconds
 Military Specifications..... Mil-A-46050C Type II, Class 2

POLYMER (Cured)

Appearance..... Colorless Solid
 Service Temperature Range -65°F to 200°F
 Softening Point..... 329°F
 Refractive Index (ND 20) 1.49
 Full Cure Time..... 24 Hours
 Dielectric Strength KV/mm 11.6
 Dielectric Constant @ 1Kc 5.4
 Coefficient of Thermal Expansion (in./in./F)000126
 Tensile Strength:
 Steel/Steel 3200 psi
 Solubility.. Nitromethane, Acetone, Dimethylformamide



DESCRIPTION

Dynatex® Super Glue is a fast setting, low to medium viscosity adhesive designed to bond close fitting surfaces quickly. **Dynatex® Super Glue** offers viscosity and flow characteristics that are ideal for filling small gaps. **Dynatex® Super Glue** sets in seconds to form a permanent, transparent bond. Effective on metal, rubber, glass aluminum, ceramics, vinyl, alloys, plastics and other non-porous surfaces.

TYPICAL APPLICATIONS

- Automotive trim
- Minor interior repairs
- knobs
- Logos
- Household repairs and more...

FEATURES

- Ready to use
- No mixing
- Permanent, transparent bond
- Fills gaps to .004"
- Holding strength to 5000 psi

PERFORMANCE OF CURED MATERIALS

(Tensile shear strength, cured for 48 hours @ 20-25°C (68-77°F))

Substrate	Range in N/mm2
Blasted Steel	19 to 26
Etched Aluminum	14 to 21
Neoprene	>10
ABS	>6
Polycarbonate	>5
PVC	>6

DIRECTIONS FOR USE

1. Make sure the surfaces to be bonded are clean and dry.
2. Dispense a drop or drops to one surface only. Apply only enough to leave a thin film after compression.
3. Press parts together and hold firmly for a few seconds. Good contact is essential. An adequate bond develops in less than one minute. (Maximum strength is achieved in 24 to 48 hours.)
4. Wipe off excess adhesive from the top of the container and recap. **Dynatex® Super Glue**, if left uncapped, may deteriorate by contamination from moisture in the air.
5. Because **Dynatex® Super Glue** condenses by polymerization, sometimes whitening will occur on the surface of the container or the bonded materials. Should this happen, wipe surfaces well with acetone.

CHEMICAL RESISTANCE

Steel to Steel.....Tensile Shear Strength

	Before Soak	After 12 Months Soak
	N/mm ²	N/mm ²
Trichloroethylene	21.17	21.17
Gasoline	21.17	21.17
Motor Oil	21.17	21.17
Water	21.17	0
10% NaOH	21.17	0
10% Hcl	21.17	0

SETTING TIME (68°F, 65% R.H.)

Steel.....	10 to 20 seconds
Aluminum.....	7 to 15 seconds
Neoprene.....	<5 seconds
ABS.....	5 to 10 seconds
Polycarbonate.....	10 to 20 seconds
PVC.....	10 to 20 seconds

STORAGE AND SHELF LIFE

When stored in the original unopened containers at or below 90°F (32°C), **Dynatex® Super Glue** has a shelf life of 12 months from date of shipment.

In Countries where high heat and humidity are a factor, special precautions must be taken. Store product in a covered, well-ventilated warehouse and avoid excessive heat conditions. Storage in high heat, high humidity conditions may reduce shelf life by up to 30%. Rotation of stock is an absolute necessity. Cartons should always be stacked upright. DO NOT stack cartons on their side. **NEVER** stack cartons more than 8 high. DO NOT store within 1 meter (4 feet) of roofline of the warehouse or storage building.

USERS PLEASE READ

The information and data contained herein is believed to be accurate and reliable; however, it is the user's responsibility to determine suitability of use. Since the supplier cannot know all the uses, or the conditions of use to which these products may be exposed, no warranties concerning the fitness or suitability for a particular use or purpose are made.

It is the user's responsibility to thoroughly test any proposed use of our products and independently conclude satisfactory performance in the application.

Likewise, if the application, product specifications or manner in which our products are used requires government approval or clearance, it is the sole responsibility of the user to obtain sure authorization.

Non-warranty: Because the storage, handling and application of the material is beyond Dynatex control, we can accept no liability for the results obtained. Dynatex sole limited warranty is the product meets the manufacturing specifications in effect at time of shipment. There is no warranty of merchantability or fitness for use, nor any other express or implied warranty. Dynatex will not be liable for incidental or consequential damages of any kind. The exclusive remedy for breach of such limited warranty is a refund of purchase price or replacement of any product shown to be other than as warranted. Suggestions of uses should not be taken as inducements to infringe any patents.

Dynatex® A division of Accumetric, LLC

Dynatex
350 Ring Road
Elizabethtown
Kentucky 42701 USA
(800) 999-2937
TEL (270) 769-5557
FAX (270) 769-6418
Outside U.S.
TEL +1(270) 769-5557
FAX +1(270) 769-6418

Accumetric Asia Pacific, LTD
18 Kitpanit Bldg. 5th Floor
#502 Patpong Road
Suriyawong, Bangrak
Bangkok, 10500 Thailand
TEL (662) 634-3060
FAX (662) 634-3066

Email: sales@dynatexinc.com
Website: www.dynatexinc.com